

**Moisture 3.5%-4.5%,
Thickness: 103-110 um
Surface roughness TS ml/min: 75-175
Surface roughness BS ml/min: 100-200
Bending stiffness MD: >110 Mn
A Grade: 102%-104% Brightness
Whiteness:150%
Substance:75/80 GSM
International standard-A4 (210mm*297mm)**

Technical Data

**Moisture 3.5%-4.5%,
Thickness: 103-110 um
Surface roughness TS ml/min: 75-175
Surface roughness BS ml/min: 100-200
Bending stiffness MD: >110 Mn
Bending stiffness CD: >50 Mn
Opacity: 95 min
CIE whiteness: 167
Cobb **Test**: 27-33 g/m² 27-33
No see through-print both sides
Guaranteed for trouble-free operation.
Capability: High Speed Copying100ppm, Laser
Capable: Inkjet Capable, Fax Capable.
High performance for both sides**